



www.sherwin-williams.com

103.31

CLASSIC 99®

INTERIOR ALKYD SEMI-GLOSS A40 SERIES

<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>	<u>SURFACE PREPARATION</u>															
<p>Classic 99 Interior Alkyd Semi-Gloss is our best quality alkyd semi-gloss product. This product is recommended for interior application on primed plaster, wall-board, wood, masonry, and primed metal.</p>	<p>Aluminum 1 ct. Galvite HS 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Galvanized Steel 1 ct. Galvite HS 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Block 1 ct. PrepRite Block Filler 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Drywall 1 ct. PrepRite Classic Latex Primer 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Plaster 1 ct. PrepRite Wall and Wood Primer 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Masonry 1 ct. PrepRite Masonry Primer 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Steel 1 ct. All Surface Enamel Primer 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p> <p>Wood, Composition Board 1 ct. PrepRite Wall and Wood Primer 2 cts. Classic 99 Interior Alkyd Semi-Gloss Enamel</p>	<p>Remove all surface contamination by washing with ProClean™ Prep Wash Concentrated Cleaner or other appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite ProBlock Primer Sealer.</p> <p>Aluminum and Galvanized Steel Wash with a ProClean Prep Wash Concentrated Cleaner to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.</p> <p>Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p> <p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer.</p> <p>Plaster Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p>															
<p>Color: Most ColorAnswers colors Coverage: 350 - 400 sq ft/gal @ 4 mils wet; 1.7 mils dry Drying Time, @ 77°F, 50% RH: temperature and humidity dependent Touch: 2-4 hours Recoat: 24 hours Flash Point: 102°F, PMCC Finish: 40-50 units @ 60° Tinting with Blend-A-Color:</p> <table border="1"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Extra White</td> <td>0-4</td> <td>100%</td> </tr> <tr> <td>Pure White</td> <td>0-4</td> <td>100%</td> </tr> <tr> <td>Midtone Base</td> <td>4-8</td> <td>100%</td> </tr> <tr> <td>Deeptone Base</td> <td>8-12</td> <td>100%</td> </tr> </tbody> </table> <p>Vehicle Type: Alkyd A40W51</p> <p>VOC: 442 gr/L; 3.69 lb/gal Volume Solids: 43 ± 2% Weight Solids: 63 ± 2% Weight per Gallon: 9.8 lb</p>	Base	oz/gal	Strength	Extra White	0-4	100%	Pure White	0-4	100%	Midtone Base	4-8	100%	Deeptone Base	8-12	100%		
Base	oz/gal	Strength															
Extra White	0-4	100%															
Pure White	0-4	100%															
Midtone Base	4-8	100%															
Deeptone Base	8-12	100%															
<p>Provides performance which is comparable to the products that are formulated in accordance with federal specification: TT-E-508C TT-E-509C</p>																	

103.31



CLASSIC 99®

INTERIOR ALKYD SEMI-GLOSS A40 SERIES

SURFACE PREPARATION

Steel

Rust and mill scale must be removed using sandpaper or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with ProClean™ Mildew Eliminator or a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

Caulking

Gaps between walls, ceilings, crown moldings, and other interior trim can be filled with Pro Select Premium Siliconized Acrylic Latex Caulk 1100A after priming the surface.

APPLICATION

Apply at temperatures above 50°F.

No reduction needed.

Brush

Use a natural bristle brush.

Roller

Use a 1/4" - 3/4" nap synthetic or lamb-swool roller cover.

Spray—Airless

Pressure2000 psi

Tip015"-.017"

CLEANUP INFORMATION

Clean spills and spatters immediately with mineral spirits. Clean tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral spirits.

MAINTENANCE

To assure maximum washability and durability, wait at least two weeks before washing the dry paint film. When removing stains, dirt, and marks, use a soft cloth or sponge with water, or use EverClean™ All Surface Cleaner or other general purpose household cleaner. Penetrating stains and marks can be removed either by applying a solution of household bleach in water and then rinsing with clean water; or, by carefully using an abrasive cleaner and water.

CAUTIONS

For exterior use on doors, trim, and other small areas of wood or metal. Do not use on the main body of exterior structures. Do not use colorants formulated for interior use only.

LABEL CAUTIONS

CAUTION contents are COMBUSTIBLE. Keep away from heat and open flame. Contains ALIPHATIC HYDROCARBONS. VAPOR HARMFUL. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. FIRST AID: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, get medical attention immediately. DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. WARNING: This product contains a chemical known to the State of California to cause cancer. DONOTTAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.
LCE 2/11/2000
02 00

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.