



PROMAR[®] 200

INTERIOR ALKYD SEMI-GLOSS

B34W200 SERIES

<u>CHARACTERISTICS</u>	<u>SPECIFICATIONS</u>	<u>SURFACE PREPARATION</u>																		
<p>ProMar 200 Interior Alkyd Semi-Gloss is a quality product designed for the professional. This product is recommended for interior application on primed plaster, wall-board, wood, masonry, and primed metal.</p> <p>Color: Most ColorAnswers[®] colors</p> <p>Coverage: Recommended: 400 sq ft/gal @4 mils wet; 1.7 mils dry</p> <p>Drying Time, @ 77°F, 50% RH: temperature and humidity dependent Touch: 2-4 hours Recoat: 24 hours</p> <p>Flash Point: 102°F (PMCC)</p> <p>Finish: 40-50 units @ 60°</p> <p>Solvent/Reducer: Mineral Spirits</p> <p>Tinting with Blend-A-Color:</p> <table border="1"> <thead> <tr> <th>Base</th> <th>oz/gal</th> <th>Strength</th> </tr> </thead> <tbody> <tr> <td>Pure White</td> <td>0-4</td> <td>100%</td> </tr> <tr> <td>Midtone Base</td> <td>4-8</td> <td>100%</td> </tr> <tr> <td>Deeptone Base</td> <td>8-12</td> <td>100%</td> </tr> <tr> <td>Luminous White</td> <td>0-5</td> <td>125%</td> </tr> <tr> <td>Package Colors</td> <td>0-4</td> <td>not controlled</td> </tr> </tbody> </table> <p>Vehicle Type: Alkyd</p> <p>VOC (as packaged): 439 grams/liter; 3.51 lbs/gal</p> <p>Volume Solids: 43 ± 2%</p> <p>Weight Solids: 63 ± 2%</p> <p>Weight per Gallon: 9.98 lb</p> <p>Provides performance which is comparable to the products that are formulated in accordance with federal specification: TT-E-508C TT-E-509C</p>	Base	oz/gal	Strength	Pure White	0-4	100%	Midtone Base	4-8	100%	Deeptone Base	8-12	100%	Luminous White	0-5	125%	Package Colors	0-4	not controlled	<p>Aluminum 1 ct. Galvite HS 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Galvanized Steel 1 ct. Galvite HS 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Block 1 ct. PrepRite Block Filler 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Drywall 1 ct. PrepRite 200 Latex Primer 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Plaster 1 ct. PrepRite Wall and Wood Primer 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Masonry 1 ct. PrepRite Masonry Primer or PrepRite Block Filler 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Steel, alkyd primer 1 ct. Kem Kromik Universal Metal Primer 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p> <p>Wood, Composition Board 1 ct. PrepRite Wall and Wood Primer 2 cts. ProMar 200 Interior Alkyd Semi-Gloss Enamel</p>	<p>Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with PrepRite ProBlock Primer Sealer.</p> <p>Aluminum & Galvanized Steel Wash with a water based degreasing cleaner to remove any oil, grease, or other surface contamination. All corrosion must be removed with sandpaper, steel wool, or other abrading method.</p> <p>Drywall Fill cracks and holes with patching paste/spackle and sand smooth. Joint compounds must be cured and sanded smooth. Remove all sanding dust.</p> <p>Masonry, Concrete, Cement, Block All new surfaces must be cured according to the supplier's recommendations—usually about 30 days. Remove all form release and curing agents. Rough surfaces can be filled to provide a smooth surface. If painting cannot wait 30 days, allow the surface to cure 7 days and prime the surface with PrepRite Masonry Primer</p> <p>Plaster Bare plaster must be cured and hard. Textured, soft, porous, or powdery plaster should be treated with a solution of 1 pint household vinegar to 1 gallon of water. Repeat until the surface is hard, rinse with clear water and allow to dry.</p>
Base	oz/gal	Strength																		
Pure White	0-4	100%																		
Midtone Base	4-8	100%																		
Deeptone Base	8-12	100%																		
Luminous White	0-5	125%																		
Package Colors	0-4	not controlled																		

103.32



PROMAR[®] 200

INTERIOR ALKYD SEMI-GLOSS

B34W200 SERIES

SURFACE PREPARATION

Steel

Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

Wood

Sand any exposed wood to a fresh surface. Patch all holes and imperfections with a wood filler or putty and sand smooth.

Mildew

Remove before painting by washing with a solution of 1 quart liquid bleach and 3 quarts of water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach/water solution.

APPLICATION

Brush

Use a natural bristle brush.

Roller

No reduction necessary. Use a 1/4" - 3/4" nap synthetic or lambswool roller cover.

Pad

No reduction necessary.

Spray—Airless

Pressure 2000 psi

Tip015"-.017"

Reduction none

Spray—Conventional

Air Pressure 40-60 psi

Fluid Pressure 20 psi

Cap/Tip 704/FX

Reduction up to 1 pint/gallon

CLEANUP INFORMATION

Clean spills and spatters immediately with mineral spirits. Clean tools immediately after use with mineral spirits. Follow manufacturer's safety recommendations when using mineral spirits.

LABEL ANALYSIS

B34W201

Pigment by Weight 35%

Titanium Dioxide 22%

Silicates 5%

Calcium Carbonate 8%

Vehicle by Weight 65%

Soya Alkyd Resin 26%

Aliphatic Solvent 36%

Additives 3%

Total 100%

CAUTIONS

For exterior use on doors, trim, and other small areas of wood or metal. Do not use on the main body of exterior structures. Do not apply at temperatures below 50°F. Non-photochemically reactive. Do not use colorants formulated for interior use only.

CAUTIONS

Contents are COMBUSTIBLE. Keep away from heat and open flame. ALIPHATIC HYDROCARBONS VAPOR HARMFUL. Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH/MSHA TC23C or equivalent) or leave the area.

Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage.

FIRST AID: In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, get medical attention immediately.

DELAYED EFFECTS FROM LONG TERM OVER-EXPOSURE. Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal.

WARNING: This product contains a chemical(s) known to the State of California to cause cancer.

DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.

A0400

The information and recommendations set forth in this Product Data Sheet are based upon tests conducted by or on behalf of The Sherwin-Williams Company. Such information and recommendations set forth herein are subject to change and pertain to the product offered at the time of publication. Consult your Sherwin-Williams representative to obtain the most recent Product Data Sheet.